TEST REPORT

DATE: 09-06-2022 **Page 1 of 1** **TEST NUMBER**: 0289067

CLIENT	Lions Floor

TEST METHOD CONDUCTED	ASTM D4060 Standard Test Method for Abrasion Resistance of Organic Coatings by the Taber Abraser

	DESCRIPTION OF TEST SAMPLE
IDENTIFICATION	Lions Floor Lone Star Spirit Collection(Packaged in Red/White/Blue Boxes)
COLOR	LI-TS106 Saddle Brownie
CONSTRUCTION	SPC
BACKING	EVA

GENERAL PRINCIPLE

A test specimen is subjected to the rubbing action of two abrading wheels under controlled conditions of pressure and abrasive action. The abrasion wheels rest on the surface of the specimen which is mounted on a rotating platform. Turning of the platform initiates the abrasive action on the test specimen.

TEST RESULTS

ABRASION WHEEL	H-18
LOAD APPLIED	1,000 Grams
NUMBER OF CYCLES	22,000

NOTE: Test sample was abraded until the color layer was visibly affected. This was considered the end point.

APPROVED BY: Gary Asbury

This facility is accredited by the National Voluntary Laboratory Accreditation Program for the specific scope of accreditation under Lab Code 100297.This accreditation does not constitute an endorsement, certification, or approval by NIST or any agency of the United States Government for the producttested. This report is provided for the exclusive use of the client to whom it is addressed. It may be used in its entirety to gain product acceptance from duly constituted authorities. This report applies only to those samples testedand is not necessarily indicative of apparently identical or similar products. This report, or the name of Professional Testing Laboratory, Inc. shall not be used under any circumstance in advertising to the general public.

714 Glenwood Place Dalton, GA 30721 706-226-3283 Fax: 706-226-6787 protest@optilink.us