



TEST REPORT

DATE: 09-06-2022

Page 1 of 1

TEST NUMBER: 0289066

| | |
|---------------|-------------|
| CLIENT | Lions Floor |
|---------------|-------------|

| | |
|------------------------------|--|
| TEST METHOD CONDUCTED | ANSI A137.1 Dynamic Coefficient of Friction of Hard Surface Floors |
|------------------------------|--|



| DESCRIPTION OF TEST SAMPLE | |
|----------------------------|--|
| IDENTIFICATION | Lions Floor Natural Essence Plus Collection (Packaged in Green/White/Blue Boxes) |
| COLOR | LI-NE208 Tresor |
| CONSTRUCTION | SPC |
| BACKING | EVA |

GENERAL PRINCIPLE

The BOT 3000E was used to determine the dynamic coefficient of friction of the test surface in a wetted condition. Distilled water/Sodium Laurel Sulfate solution was used to wet out the test area. The test device was fitted with the SBR slider and was used on all replications. The individual values were averaged.

TEST RESULTS

| | |
|-------------------------|--|
| SAMPLE CONDITION | Wet with Distilled Water and 0.05% Sodium Laurel Sulfate |
|-------------------------|--|

| SAMPLE 1 | SAMPLE 2 | SAMPLE 3 |
|---------------------|----------|-------------|
| 0.48 | 0.47 | 0.47 |
| AVERAGE DCOF | | 0.47 |

APPROVED BY:

This report is provided for the exclusive use of the client to whom it is addressed. It may be used in its entirety to gain product acceptance from duly constituted authorities. This report applies only to those samples tested and is not necessarily indicative of apparently identical of similar products. This report, or the name of Professional Testing Laboratory Inc. shall not be used under any circumstance in advertising to the general public.