

## **TEST REPORT**

**CLIENT** Lions Floor

TEST METHOD CONDUCTED

ISO 24337 Laminate Floor Coverings - Determination of Geometrical Characteristics

DESCRIPTION OF TEST SAMPLE		
IDENTIFICATION	Lions Floor Trenta Collection	
CONSTRUCTION	SPC	
BACKING	EVA	

## **GENERAL PRINCIPLE**

The submitted goods were measured to determine geometrical values for size, squareness, straightness, height deviations, and gapping when applied together. All values listed are in mm.

## **TEST RESULTS**

CHARACTERISTIC	VALUE (mm)
Width Flatness	Max: 0.153 (0.066%) / Avg: 0.129 (0.056%) - Concave
Length Flatness	Max: 0.974 (0.063%) / Avg: 0.742 (0.048%) - Concave
Openings Between Elements	Max: 0.153 / Avg: 0.091
Height Difference Between Elements	Max: 0.141 / Avg: 0.097

APPROVED BY:

This report is provided for the exclusive use of the client to whom it is addressed. It may be used in its entirety to gain product acceptance from duly constituted authorities. This report applies only to those samples tested and is not necessarily indicative of apparently identical of similar products. This report, or the name of Professional Testing Laboratory Inc. shall not be used under any circumstance in advertising to the general public.

Lang asleny

714 Glernwood Place Dalton, GA 30721 Phone: 706-226-3283 Fax: 706-226-6787 email: protest@optilink.us