

## **TEST REPORT**

Test Method for Peel or Stripping Strength
T

# 

DESCRIPTION OF TEST SAMPLE		
IDENTIFICATION	Uptown: 2.5mm/12mil LVP	
COLOR	East Aspen	
ROLL NUMBER	SKU: LI-UP07	
CONSTRUCTION	LVP	

#### **GENERAL PRINCIPLE**

This test method covers the determination of the comparative peel or stripping characteristics of adhesive bonds when tested on a one inch wide specimen after being applied for 10 days and conditioned in laboratory conditions of 70° F and 50% relative humidity. Samples were tested at 6.0 inches per minute cross head speed.

#### TEST RESULTS

SPECIMEN 9 SPECIMEN 10	8.3 Lbs./Inch 8.5 Lbs./Inch
SPECIMEN 8	8.4 Lbs./Inch
SPECIMEN 7	8.7 Lbs./Inch
SPECIMEN 6	8.9 Lbs./Inch
SPECIMEN 5	8.3 Lbs./Inch
SPECIMEN 4	8.5 Lbs./Inch
SPECIMEN 3	8.6 Lbs./Inch
SPECIMEN 2	9.1 Lbs./Inch
SPECIMEN 1	8.8 Lbs./Inch

Lang atlury APPROVED BY:

This report is provided for the exclusive use of the client to whom it is addressed. It may be used in its entirety to gain product acceptance from duly constituted authorities. This report applies only to those samples tested and is not necessarily indicative of apparently identical of similar products. This report, or the name of Professional Testing Laboratory Inc. shall not be used under any circumstance in advertising to the general public.



## **TEST REPORT**

DATE: 03-23-2023	Page 2 of 2	<b>TEST NUMBER</b> : 0295654
CLIENT	Lions Floor	
TEST METHOD CONDUCTED	ASTM D903 Standard Test Metho	od for Peel or Stripping Strength

of Adhesive Bonds

## 

DESCRIPTION OF TEST SAMPLE		
IDENTIFICATION	Uptown: 2.5mm/12mil LVP	
COLOR	East Aspen	
ROLL NUMBER	SKU: LI-UP07	
CONSTRUCTION	LVP	



### APPROVED BY:

This report is provided for the exclusive use of the client to whom it is addressed. It may be used in its entirety to gain product acceptance from duly constituted authorities. This report applies only to those samples tested and is not necessarily indicative of apparently identical of similar products. This report, or the name of Professional Testing Laboratory Inc. shall not be used under any circumstance in advertising to the general public.

Lang atluny