



TEST REPORT

DATE: 03-23-2023

Page 1 of 1

TEST NUMBER: 0295654

CLIENT	Lions Floor
---------------	-------------

TEST METHOD CONDUCTED	ASTM F1914 Test Method for Short-Term Indentation and Residual Indentation of Resilient Floor Covering
------------------------------	--



DESCRIPTION OF TEST SAMPLE	
IDENTIFICATION	Uptown: 2.5mm/12mil LVP
COLOR	East Aspen
ROLL NUMBER	SKU: LI-UP07
CONSTRUCTION	LVP

PROCEDURE

A test sample is loaded with 140 lbs. on a presser foot .178 inches in diameter for 10 minutes. After 60 minutes of recovery time the indentation is measured again and compared to the original thickness of the sample.

TEST RESULTS

RESIDUAL INDENTATION AT 140 Lbs.	0.006 Inch (6.06%)
---	--------------------



APPROVED BY:

This report is provided for the exclusive use of the client to whom it is addressed. It may be used in its entirety to gain product acceptance from duly constituted authorities. This report applies only to those samples tested and is not necessarily indicative of apparently identical of similar products. This report, or the name of Professional Testing Laboratory Inc. shall not be used under any circumstance in advertising to the general public.