

TEST REPORT

DATE: 09-06-2022	Page 1 of 1	TEST NUMBER : 0289068
CLIENT	Lions Floor	
TEST METHOD CONDUCTED	ASTM D2047 James Machine - Coefficient of Friction on Flooring Material	

DESCRIPTION OF TEST SAMPLE			
IDENTIFICATION	Lions Floor Lone Star Spirit XL Collection (Packaged in Red/White/Blue Boxes)		
COLOR	LI-TS206 Shangri La		
CONSTRUCTION	SPC		
BACKING	EVA		

GENERAL PRINCIPLE

This test was used to measure the relative static coefficient of friction by using the James Machine.

TEST RESULTS

TEST ENVIRONMENT	69° F 50% Relative Humidity
Sensor Materials	Dry
Standard Neolite	0.93

Lary atlury APPROVED BY:

This report is provided for the exclusive use of the client to whom it is addressed. It may be used in its entirety to gain product acceptance from duly constituted authorities. This report applies only to those samples tested and is not necessarily indicative of apparently identical of similar products. This report, or the name of Professional Testing Laboratory Inc. shall not be used under any circumstance in advertising to the general public.